

Revision Date: December 2021 Version: 1.2

Phone: +39 0362 1547305

Fax: +39 039 8942754

MB PE BATO 31

HALOGENATED FLAME RETARDANT MASTERBATCH

MB PE BATO 31 is a flame retardant masterbatch containing a brominated flame retardant combined with an antimony trioxide synergist in a PE matrix. MB PE BATO 31 has a high resistance to UV radiation and excellent thermal stability. MB PE BATO 31 does not present blooming effects, which makes it a suitable flame retardant for polyolefin film. Its excellent electrical properties make it ideal for cable applications. MB PE BATO 31 is mainly used in engineering polymers such as polyolefin, high-impact polystyrene (HIPS), thermoplastic polyesters (PBT, PET), polycarbonate and elastomers.

PHYSICAL-CHEMICAL PROPERTIES

Appearance Granules

Color Off white

Bulk density, g/cm3 1.0±0.2

Volatiles, ppm Max.3000

HANDLING AND STORAGE: The processing and use of MB PE BATO 31 requires adequate technical and

professional knowledge. Please consult safety data sheet for further handling,

storage and toxicity information.

MB PE BATO 31 has to be stored in tightly sealed original container in a cool and

well-ventilated area, away from direct sunlight.

PACKAGING: Standard packaging of MB PE BATO 31 is in 25 Kg in plastic bags.

DISCLAIMER:

Information contained in this document is provided to the best of our knowledge and is considered true as per revision date. We do not accept any liability for loss and damage that may occur from the improperly use of this information and for the use against the safety legal requirements and patent rights. This specification does not release the customer from the obligation to check the product as to its suitability for intended area of usage.